

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
10 January 2002 (10.01.2002)

PCT

(10) International Publication Number
WO 02/02698 A1

(51) International Patent Classification⁷: C09D 5/16

(21) International Application Number: PCT/EP01/07227

(22) International Filing Date: 26 June 2001 (26.06.2001)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
00305726.2 6 July 2000 (06.07.2000) EP

(71) Applicant: INTERNATIONAL COATINGS LIMITED
[GB/GB]; Oriel House, 16 Connaught Place, London W2
2ZB (GB).

(72) Inventors: LINES, Robert; 14 Parklands, Northumber-
land, Ponteland NE20 9LL (GB). FINNIE, Alistair, An-
drew; 11 Felton Avenue, Whitley Bay, Tyne & Wear NE25
8TQ (GB). FOX, John; 14 Burlington Court, Hadrian Park
Estate, Wallsend, Tyne & Wear NE28 9YH (GB).

(74) Agent: SCHALKWIJK, Pieter, Cornelis; Akzo Nobel
N.V., Intellectual Property Dept. (Dept. AIP), P.O. Box
9300, NL-800 SB Arnhem (NL).

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU,
AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU,
CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH,
GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC,
LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW,
MX, MZ, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK,
SL, TJ, TM, TR, TT, TZ, UA, UG, UZ, VN, YU, ZA, ZW.

(84) Designated States (*regional*): ARIPO patent (GH, GM,
KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian
patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European
patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE,
IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF,
CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).

Published:

— with international search report

For two-letter codes and other abbreviations, refer to the "Guid-
ance Notes on Codes and Abbreviations" appearing at the begin-
ning of each regular issue of the PCT Gazette.

(54) Title: ANTIFOULING PAINT

(57) Abstract: The invention relates to an antifouling paint having a binder comprising a rosin material and an auxiliary film-forming resin, the paint including an ingredient having marine biocide properties, wherein the binder comprises a blend of the rosin material and an auxiliary film-forming resin in ratio 20:80 to 95:5 % by weight, the auxiliary film-forming resin comprising 20-100 % by weight of an acid-functional film forming polymer (A) whose acid groups are blocked by groups capable of hydrolyzing, dissociating or exchanging with seawater species to leave a polymer soluble in seawater, the blocking groups being selected from quaternary ammonium groups which form a quaternary ammonium salt of the polymer and quaternary phosphonium groups which form a quaternary phosphonium salt of the polymer, and 80-20 % of a non-hydrolyzing water-insoluble film-forming polymer (B).

WO 02/02698 A1



ANTIFOULING PAINT

- 5 This invention relates to antifouling paint. An antifouling paint is used as a top coat on ships' hulls to inhibit the settlement and growth of marine organisms such as barnacles and algae, generally by release of a biocide for the marine organisms.
- 10 Traditionally, antifouling paints have comprised a relatively inert binder with a biocidal pigment which is leached from the paint. Among the binders which have been used are vinyl resins and rosin. The vinyl resins are seawater-insoluble and paints based on them use a high pigment concentration so that there is contact between pigment particles to ensure
- 15 leaching. Rosin is a hard brittle resin which is very slightly soluble in seawater. Rosin-based antifouling paints have been referred to as soluble matrix or eroding paints. The biocidal pigment is very gradually leached out of the matrix of rosin binder in use, leaving a skeletal matrix of rosin which becomes washed off the hull surface to allow leaching of the biocidal
- 20 pigment from deep within the paint film.

Many successful antifouling paints in recent years have been "self-polishing copolymer" paints based on a polymeric binder to which biocidal tri-organotin moieties are chemically bound and from which the biocidal

25 moieties are gradually hydrolyzed by seawater, as described for example in GB-A-1457590. Self-polishing copolymer paints which release non-biocidal moieties are described in EP-A-69559, EP-A-204456, EP-A-529693, EP-A-779304, WO-A-91/14743, WO-A-91/09915, GB-A-231070 and JP-A-9-286933.

30

US-A-4675051 describes a marine antifouling paint which is gradually dissolved in seawater and which comprises a binder which is a resin

CONFIRMATION COPY

produced by the reaction of rosin and an aliphatic polyamine containing at least one primary or secondary amine group. EP-A-802243 describes a coating composition comprising a rosin compound, a polymer containing organosilyl ester groups and an antifoulant.

5

Rosin is not a very good film-former, and it is known to add other film-forming resins to rosin based antifouling paints. This has sometimes led to paints which were difficult to wash off the hull surface. The present invention seeks to improve rosin-based antifouling paints with respect to the
10 strength of the paint film and/or the reliable eroding away of the rosin-based paint matrix after biocide has been leached from the paint.

An antifouling paint according to the present invention has a binder comprising a rosin material and an auxiliary film-forming resin, the paint
15 including an ingredient having marine biocide properties, characterized in that the binder comprises a blend of the rosin material and an auxiliary film-forming resin in ratio 20:80 to 95:5% by weight, the auxiliary film-forming resin comprising 20-100% by weight of an acid-functional film forming polymer (A) whose acid groups are blocked by groups capable of
20 hydrolyzing, dissociating or exchanging with seawater species to leave a polymer soluble in seawater, the blocking groups being selected from quaternary ammonium groups which form a quaternary ammonium salt of the polymer and quaternary phosphonium groups which form a quaternary phosphonium salt of the polymer, and 80-20% of a non-hydrolyzing water-
25 insoluble film-forming polymer (B).

The rosin material is preferably rosin, particularly wood rosin or alternatively tall rosin or gum rosin. The main chemical constituent of rosin is abietic acid. The rosin can be any of the grades sold commercially, preferably that
30 sold as WW (water white) rosin. The rosin material can alternatively be a rosin derivative, for example a maleinised or fumarised rosin, hydrogenated

rosin, formylated rosin or polymerised rosin, or a rosin metal salt such as calcium, magnesium, copper or zinc rosinate.

The acid-functional film forming polymer (A) whose acid groups are blocked
5 by groups capable of hydrolyzing, dissociating or exchanging with seawater species to leave a polymer soluble in seawater is preferably an acid-functional polymer whose acid groups are blocked by quaternary ammonium groups which form a quaternary ammonium salt of the polymer. The quaternary ammonium group can be tetra-alkyl or it can contain one or
10 more alkoxyalkyl, cycloalkyl, aryl or aralkyl groups. More generally the organic groups in the quaternary ammonium group may be saturated or unsaturated, aliphatic, cycloaliphatic, aromatic, aliphatic-aromatic or heterocyclic.

15 The quaternary ammonium moiety preferably contains at least one organic group containing at least 3 carbon atoms, advantageously at least 8 carbon atoms and preferably from 8 to 25 carbon atoms (for example 8 to 20 carbon atoms), and more especially from 12 to 25 carbon atoms. The polymers containing a relatively long chain quaternary ammonium group
20 have a decreased rate of dissolution in seawater. Examples of such quaternary ammonium groups are dodecyl trimethyl ammonium, hexadecyl trimethyl ammonium, octadecyl trimethyl ammonium, oleyl trimethyl ammonium, benzyl dodecyl dimethyl ammonium, dodecyl dimethyl octyl ammonium or trioctyl methyl ammonium. Mixtures of quaternary ammonium
25 groups can be used; for example an organic group having 8 to 20 carbon atoms can be derived from a naturally occurring material such as a natural fatty material. Examples of such mixed quaternary ammonium groups are trimethyl hydrogenated tallow ammonium, dimethyl di(hydrogenated tallow) ammonium or trimethyl coconut ammonium. The quaternary group can
30 alternatively be derived from rosin, for example it can be the N,N,N-trimethyl derivative of the amine sold commercially as "Rosin Amine D",

being mainly dehydroabietyl trimethyl ammonium. Advantageously, the total number of carbon atoms in the quaternary ammonium moiety is 8 or more, preferably 12 or more (for example, from 12 to 40).

5 The acid-functional film forming polymer (A) whose acid groups are blocked by groups capable of hydrolyzing, dissociating or exchanging with seawater species to leave a polymer soluble in seawater is alternatively an acid-functional polymer whose acid groups are blocked by quaternary phosphonium groups which form a quaternary phosphonium salt of the
10 polymer. The quaternary phosphonium group can be tetra-alkyl or it can contain one or more alkoxyalkyl, cycloalkyl, aryl or aralkyl groups. More generally the organic groups in the quaternary phosphonium group may be saturated or unsaturated, aliphatic, cycloaliphatic, aromatic, aliphatic-aromatic or heterocyclic. Examples of such quaternary phosphonium
15 groups are tetrabutylphosphonium, tetraphenylphosphonium and stearyltributylphosphonium.

The acid-functional polymer is preferably an addition copolymer of an olefinically unsaturated carboxylic acid, sulphonic acid, acid sulphate ester,
20 phosphonic acid or acid phosphate ester and at least one unsaturated comonomer. The unsaturated carboxylic acid can for example be acrylic or methacrylic acid or an acid functional ester or amide of acrylic acid or methacrylic acid such as mono-2-(methacryloyloxy)ethyl succinate, mono-2-(methacryloyloxy)ethyl phthalate, 2-acrylamidoglycolic acid, or 3-
25 acrylamido-3-methylbutyric acid. The unsaturated sulphonic acid can for example be 2-acrylamido-2-methylsulphonic acid (AMPS). The unsaturated comonomer can for example be an ester or amide of an alkyl, alkoxyalkyl, carbocyclic or heterocyclic alcohol or amine with an unsaturated carboxylic acid, such as methyl acrylate or methacrylate, butyl acrylate or
30 methacrylate and isobornyl acrylate or methacrylate and the like.

Alternatively the unsaturated co-monomer may be a vinylic compound, for example styrene, vinyl pyrrolidone or vinyl acetate.

The acid-functional film forming polymer (A) whose acid groups are blocked
5 by quaternary ammonium groups which form a quaternary ammonium salt of the polymer can be prepared by reaction of a polymer containing acid or acid-salt groups with a quaternary ammonium compound. Alternatively, it can be prepared by polymerisation of a quaternary ammonium salt of an ethylenically unsaturated acid-functional monomer formed, for example, by
10 reaction of an ethylenically unsaturated monomer containing acid or acid-salt groups with a quaternary ammonium compound. Examples of suitable acid-salts groups include metal salts such as sodium, potassium and lithium salts, or amine salts such as ammonium or hydroxyethyldimethylammonium salts and the like. Examples of suitable quaternary ammonium compounds
15 include quaternary ammonium hydroxides, carbonates, bicarbonates, sulphates, bisulphates or halides.

The acid-functional film forming polymer (A) whose acid groups are blocked
by quaternary phosphonium groups which form a quaternary phosphonium
20 salt of the polymer can be prepared by similar methods to those used to prepare the acid-functional film forming polymer (A) whose acid groups are blocked by quaternary ammonium groups, using a quaternary phosphonium compound in place of the quaternary ammonium compound.

25 As a further possibility, when the acid-functional film forming polymer (A) whose acid groups are blocked by quaternary ammonium or quaternary phosphonium groups is a copolymer of an olefinically unsaturated sulphonic acid, the quaternary ammonium or quaternary phosphonium group may be introduced by reaction of a sulphonate ester, for example a
30 methylsulphonate ester, with a tertiary amine or tertiary phosphine. The sulphonate ester may be in monomeric or polymeric form. If the ester is in

monomeric form, the resulting quaternary ammonium or quaternary phosphonium salt of an olefinically unsaturated sulphonic acid-functional monomer is then polymerised for use according to the present invention.

- 5 The non-hydrolyzing water-insoluble film-forming polymer (B) can for example be a vinyl ether polymer, for example a poly(vinyl alkyl ether) or a copolymer of a vinyl alkyl ether with vinyl acetate or vinyl chloride, an acrylate ester polymer such as a homopolymer or copolymer of one or more alkyl acrylates or methacrylates which preferably contain 1 to 6
10 carbon atoms in the alkyl group and may contain a co-monomer such as acrylonitrile or styrene, or a vinyl acetate polymer such as polyvinyl acetate or a vinyl acetate vinyl chloride copolymer. The polymer (B) can alternatively be a polyamine, particularly a polyamide having a plasticising effect such as a polyamide of a fatty acid dimer or the polyamide sold under
15 the Trademark "Santiciser".

We have found that the paints of the invention have the optimum combination of film-forming and eroding properties when the non-hydrolyzing water-insoluble film-forming polymer (B) is present in the
20 composition, albeit as a minor proportion of the auxiliary film-forming resin. Most preferably the weight ratio of rosin to total auxiliary film-forming resin is from 25:75, 50:50 or 55:45 up to 80:20. The hydrolyzing or dissociating film-forming polymer (A) preferably forms at least 30, most preferably at least 50, up to 80 or 90% by weight of the auxiliary film-forming resin, the
25 non-hydrolyzing water-insoluble polymer (B) being the remainder.

The antifouling paint can include a non-polymeric plasticiser. Such a plasticiser can for example be present at up to 50% by weight based on the total binder polymer, most preferably at least 10% and up to 35% by weight
30 based on binder polymer. Examples of such plasticisers are phthalate esters such as dibutyl phthalate, butyl benzyl phthalate or dioctyl phthalate,

phosphate triesters such as tricresyl or tris(isopropyl)phenyl phosphate, or chlorinated paraffins.

The rosin and the polymers forming the auxiliary film-forming resin can be
5 mixed in a common solvent which forms at least part of the paint solvent,
for example an aromatic hydrocarbon such as xylene, toluene or
trimethylbenzene, an alcohol such as n-butanol, an ether alcohol such as
butoxyethanol or methoxypropanol, an ester such as butyl acetate or
isoamyl acetate, an ether-ester such as ethoxyethyl acetate or
10 methoxypropyl acetate, a ketone such as methyl isobutyl ketone or methyl
isoamyl ketone, an aliphatic hydrocarbon such as white spirit, or a mixture
of two or more of these solvents. The paint can alternatively be water-
based, for example it can be based on a commercial aqueous rosin
dispersion.

15

The ingredient having marine biocidal properties usually is a biocide for
aquatic organisms or a pigment. This biocide or pigment can be mixed with
the binder using conventional paint-blending techniques. The biocide may
itself be all or part of the pigment of the paint. The coating composition
20 preferably has a pigment volume concentration of, for example, 15 to 55%.
The pigment preferably comprises at least one sparingly soluble
metalliferous pigment having a solubility in seawater of from 0.5 to 10 parts
per million by weight. Examples of such pigments which are also aquatic
biocides include copper or zinc compounds, such as cuprous oxide,
25 cuprous thiocyanate, cuprous sulphate, zinc ethylene bis(dithiocarbamate),
zinc dimethyl dithiocarbamate, zinc pyrithione, copper pyrithione, zinc
diethyl dithiocarbamate, copper resinate or cuprous ethylene
bis(dithiocarbamate). Other sparingly soluble pigments having a solubility in
sea water of 0.5 to 10 parts per million include barium sulphate, calcium
30 sulphate, dolomite and zinc oxide. Mixtures of sparingly soluble pigments
can be used, for example cuprous oxide, cuprous thiocyanate or zinc

ethylene bis(dithiocarbamate), which are highly effective biocidal pigments, can be mixed with zinc oxide, which is not effective as a biocide but dissolves slightly more rapidly in seawater. Copper metal can be present as an aquatic biocide, for example in flake or powder form.

5

The antifouling coating composition can contain a non-metalliferous biocide for marine organisms, for example tetramethyl thiuram disulphide, methylene bis(thiocyanate), captan, pyridiniumtriphenylboron, a substituted isothiazolone such as 4,5-dichloro-2-n-octyl-4-isothiazolin-3-one, 2-
10 methylthio-4-t.butylamino-6-cyclopropylamino-s-triazine, N-3,4 dichlorophenyl-N',N'-dimethyl-urea ("Diuron"), 2-(thio-cyanomethylthio) benzothiazole, 2,4,5,6-tetrachloro-isophthalonitrile, dichlorofluanid, tolylfluanid or 2,3,5,6-tetrachloro-4-(methyl-sulphonyl)pyridine. Such a non-metalliferous biocide can be used as the only biocide of the coating in a
15 copper-free, or even metal-free or pigment-free, antifouling coating. Many of these non-metalliferous biocides are solid and all are sparingly soluble in seawater and may help the "self-polishing" action of the paint.

The coating composition can additionally contain a pigment which is not
20 reactive with seawater and may be highly insoluble in seawater (solubility below 0.5 part per million by weight) such as titanium dioxide or ferric oxide or an organic pigment such as phthalocyanine or azo pigment. Such highly insoluble pigments are preferably used at less than 60% by weight of the total pigment component of the paint, most preferably less than 40%. The
25 coating composition can additionally contain conventional thickeners, particularly thixotropes such as silica or bentonite and/or stabilisers, for example zeolites or aliphatic or aromatic amines such as dehydroabietylamine.

The invention will be elucidated with reference to the following examples. These are intended to illustrate the invention but are not to be construed as limiting in any manner the scope thereof.

5

Examples

The following materials were mixed in the stated % by weight in a high speed disperser to form antifouling paints according to the invention.

10

Compound	Example No.:	
	1	2
Rosin	9.96	9.96
Hydrolysable acrylic Polymer (A1)	5.49	-
Hydrolysable acrylic Polymer (A2)	-	5.49
Non-hydrolyzing acrylic polymer (B1)	2.62	2.62
Tris(isopropylphenyl) phosphate plasticiser	5.09	5.09
Red copper oxide	37.48	37.48
Zinc Oxide	11.85	11.85
Zinc ethylene bis(dithiocarbamate)	2.05	2.05
Copper pyrithione	1.98	1.98
Natural iron oxide	3.16	3.16
Solvent	17.64	17.64
Additives	2.68	2.68

Acrylic polymer A1 is a copolymer of the trimethyl (hydrogenated tallow) ammonium salt of mono-2-(methacryloyloxy) ethylsuccinate, styrene and isobornyl methacrylate in the mole ratio 25.0:30.0:45.0.

15

Acrylic polymer A2 is a copolymer of the hexadecyltrimethylammonium salt of 2-acrylamido-2-methylpropanesulphonic acid, isobornyl methacrylate and isobornyl acrylate in mole ratio 27.5:47.5:25.

- 5 Acrylic polymer B1 is a n-butyl acrylate polymer sold under the Trademark "Acronal 4F".

The solvent comprised mainly xylene with minor amounts of methyl isoamyl ketone, methyl isobutyl ketone and n-butanol. The rosin and acrylic polymers
10 were dissolved in solvent before being mixed with the other paint ingredients.

Additives comprised an organo-clay structuring agent, silica, carbon black and molecular sieve zeolite.

- 15 As a test of antifouling performance the paints of Examples 1 and 2 were each applied to plywood boards which had been pre-painted with a commercial anti-corrosive primer and the boards were immersed in the sea at Newton Ferrers, Devon, England. As a comparative test, primed boards were coated with a rosin paint having a formulation similar to Example 1 but containing extra
20 "Acronal 4F" in place of the hydrolysable acrylic polymer. The paint films were periodically assessed for settlement of marine fouling organisms and the results are shown below.

In all results quoted below, 100 = Totally clean, 0 = Totally fouled.

25

Example	Average fouling rating
1	83
2	88
Comparative	60

Claims

1. An antifouling paint having a binder comprising a rosin material and an auxiliary film-forming resin, the paint including an ingredient having marine biocide properties, characterised in that the binder comprises a blend of the rosin material and an auxiliary film-forming resin in ratio 20:80 to 95:5% by weight, the auxiliary film-forming resin comprising 20-100% by weight of an acid-functional film forming polymer (A) whose acid groups are blocked by groups capable of hydrolyzing, dissociating or exchanging with seawater species to leave a polymer soluble in seawater, the blocking groups being selected from quaternary ammonium groups which form a quaternary ammonium salt of the polymer and quaternary phosphonium groups which form a quaternary phosphonium salt of the polymer, and 80-20% of a non-hydrolyzing water-insoluble film-forming polymer (B).
2. An antifouling paint according to claim 1 characterised in that the rosin material is rosin.
3. An antifouling paint according to claim 1 or claim 2, characterised in that the binder comprises a blend of the rosin material and the auxiliary film-forming resin in a ratio of 55:45 to 80:20 by weight.
4. An antifouling paint according to any one of claims 1 to 3, characterised in that the auxiliary film-forming resin comprises 30-90% by weight of the film-forming polymer (A) capable of hydrolyzing or dissociating to a polymer soluble in sea water and 70-10% by weight of the non-hydrolyzing water-insoluble film-forming polymer (B).
5. An antifouling paint according to any one of claims 1 to 4, characterised in that the film-forming polymer (A) is a quaternary ammonium salt of an

addition copolymer of an olefinically unsaturated sulphonic acid or acid sulphate ester and at least one olefinically unsaturated co-monomer.

- 5 6. An antifouling paint according to any one of claims 1 to 4, characterised in that the film-forming polymer (A) is a quaternary ammonium salt of an addition copolymer of an olefinically unsaturated carboxylic acid and at least one olefinically unsaturated co-monomer.
- 10 7. An antifouling paint according to claim 5 or claim 6, characterised in that the quaternary ammonium group contains at least one aliphatic hydrocarbon group having 8 to 25 carbon atoms.
- 15 8. An antifouling paint according to any one of claims 1 to 7, characterised in that the non-hydrolyzing water-insoluble film-forming polymer (B) is an acrylate ester polymer or a vinyl ether polymer.
9. An antifouling paint according to any of one claims 1 to 8, characterised in that the binder includes a non-polymeric plasticiser present at up to 50% by weight based on the total binder polymer.

INTERNATIONAL SEARCH REPORT

Int Application No
PCT/EP 01/07227A. CLASSIFICATION OF SUBJECT MATTER
IPC 7 C09D5/16

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 7 C09D

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the International search (name of data base and, where practical, search terms used)

PAJ, EPO-Internal, WPI Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	PATENT ABSTRACTS OF JAPAN vol. 013, no. 384 (C-629), 24 August 1989 (1989-08-24) & JP 01 131286 A (DAINIPPON INK & CHEM INC; OTHERS: 01), 24 May 1989 (1989-05-24) abstract	1
A	PATENT ABSTRACTS OF JAPAN vol. 009, no. 145 (C-287), 20 June 1985 (1985-06-20) & JP 60 028456 A (NIPPON YUSHI KK), 13 February 1985 (1985-02-13) abstract	1
A	US 4 221 839 A (M&T CHEMICALS INC.) 9 September 1980 (1980-09-09) claims	1
	--- -/-	

☒ Further documents are listed in the continuation of box C.☒ Patent family members are listed in annex.

* Special categories of cited documents:

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *&* document member of the same patent family

Date of the actual completion of the international search

2 October 2001

Date of mailing of the international search report

17/10/2001

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax (+31-70) 340-3016

Authorized officer

Girard, Y

INTERNATIONAL SEARCH REPORT

In ~~Patent~~ Application No
PCT/EP 01/07227

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 5 302 192 A (COURTAULDS COATINGS) 12 April 1994 (1994-04-12) abstract -----	1

INTERNATIONAL SEARCH REPORT

 Int'l Application No
 PCT/JP 01/07227

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
JP 01131286	A	24-05-1989	JP 2614467 B2	28-05-1997
JP 60028456	A	13-02-1985	NONE	
US 4221839	A	09-09-1980	NL 7703305 A	02-10-1978
			AU 523839 B2	19-08-1982
			AU 3446978 A	27-09-1979
			BE 865294 A2	17-07-1978
			CA 1111981 A1	03-11-1981
			DE 2812602 A1	05-10-1978
			DK 128578 A	29-09-1978
			FR 2385779 A1	27-10-1978
			GB 1584943 A	18-02-1981
			IT 1218833 B	24-04-1990
			JP 53127534 A	07-11-1978
			NO 780987 A ,B,	29-09-1978
			PT 67767 A	01-04-1978
US 5302192	A	12-04-1994	AT 141317 T	15-08-1996
			BR 9007943 A	06-10-1992
			DE 69028116 D1	19-09-1996
			DE 69028116 T2	13-02-1997
			DK 506782 T3	14-10-1996
			EP 0506782 A1	07-10-1992
			ES 2091909 T3	16-11-1996
			WO 9109915 A1	11-07-1991
			GR 3021554 T3	28-02-1997
			JP 2994749 B2	27-12-1999
			JP 5504365 T	08-07-1993
			NO 303583 B1	03-08-1998
			PT 96346 A ,B	15-10-1991
			SG 45228 A1	16-01-1998